

PERFORMANCE DATA – InfraCOOL™ Heritage Red vs Std Heritage Red

KEY FACTS : HEAT REFLECTIVE COATINGS

- Due to their large surface area and exposure, Roof Surfaces capture enormous amounts of the suns energy and thus COOL ROOFS offer potential energy savings of 10-30%*, resulting in direct cost and green house gas emission savings
- Dulux® InfraCOOL™ technology works by maximising the TOTAL SOLAR REFLECTION including the (invisible) infra-red portion of the suns energy which accounts for over 50% of the suns total light energy
- Various internationally accepted verification methods demonstrate the direct benefits of InfraCool technology in comparative testing vs comparable std colour and/or surface materials

ASTM E1980-01 : SOLAR REFLECTANCE INDEX

The following comparative test data (based on constant solar conditions) demonstrates the calculated surface temperature cooling benefit using Dulux® InfraCOOL™ technology against the nominated system.

Total Solar Reflectance <i>Reflectance of the suns energy across the broad solar spectrum including</i>	% TSR ASTM E903 or C1549			Dulux® AcraTex® COOL ROOF Heritage Red		
	<i>visible region , defining the colour we see</i>					
• <i>non visible region, mainly Infra-red (approx 50% of Total Suns rays)</i>						
Thermal Emittance <i>The ability of a material to release (ie. emit) captured heat energy</i>	0-1 scale, ASTM C1371			0.90		
	<i>Wind condition...</i>			<i>low</i>	<i>medium</i>	<i>high</i>
Solar Reflectance Index <i>relevant to wind conditions</i>	37.52	37.99	38.41	37.52	37.99	38.41
Surface Temperature <i>constant air temperature : 37C constant Solar flux : 1000 W/m2</i>	83	68	53	83	68	53
InfraCOOL™ effect <i>potential surface temp. COOLING</i>				0°C COOLER <i>low wind conditions</i>		


ASTM E903 : SOLAR ABSORBANCE

TSR and Spectral Reflectance is tested in accordance with ASTM E-903.

% Reflectance of 2 visually equal panels reported at individual wavelengths from 200-2500 nanometers.

Results:

- ❖ Reflectance across the visible and invisible light regions were very similar
- ❖ TSR (Total Solar Reflectance) did not increase with InfraCOOL Technology as standard formula 962 Roof Membrane is already optimized for Solar Reflection



COLOUR CLASSIFICATIONS :

Solar Absorbance (SA)		Building Code of Australia (BCA) Classification			NSW Building & Sustainability Index (BASIX) Classification		
Std (SA)	InfraCOOL™ (SA)	Criteria (SA)	STD rating	InfraCOOL™ rating	Criteria (SA)	STD rating	InfraCOOL™ rating
0.655	0.655	Light : <0.55 Dark : >0.55	DARK	DARK	Light: <0.475 Medium: 0.475-0.70 Dark : >0.70	MEDIUM	MEDIUM

* Energy saving potential based on Field Study of 2 identical buildings with constant state air-conditioning. High reflectance white coating vs original dark roofing surface
Technical Report : ICHeritageRed-01

InfraCOOL™...Colours that shield from the sun